

**Chemical Resistance Data**

※The following table should be referred to select a hose for a specific working fluid.

- ◎=Excellent, can be used without problems.
- =Good, may be affected to same extent, but can be used under general conditions.
- △=Fair, need to verify suitability.
- ×=Poor, cannot be used.

	Product	Soft PVC	Polyolefin	Silicon Rubber	Fluoride Polymer (ETFE)
		TOYORON SUPER TOYORON TOYOSIGNAL TOYOSPRING TOYORING	ECORON ECORON-S (Inner layer)	TOYOSILICONE TOYOSILICONE-S TOYOSILICONE-P	TOYOFUSSO TOYOFUSSO-E (Most Inner layer)
	Chemical Name				
	Tannic acid			○	
	Tar	×		○	
	Tartaric acid			◎	
	Tetrachloroethylene	×	△	○	◎
	Tetraethyl lead		○	×	
	Tetrahydrofuran	×	△	×	◎
	Tetralin			△	
	Thionyl chloride	×			
	Tin(II)chloride	△	○	○	◎
T	Toluene	×	△	×	◎
	Trichloroacetic acid				◎
	Trichloroethylene	×		×	◎
	Tricresyl phosphate			△	
	Triethanolamine			×	
	Triethylamine				◎
	Turbine oil	×			
	Turpentine oil	△		×	
V	Vinegar	○	◎		
W	Water	◎	◎	○	◎
	Whiskey,Wine		○	◎	
X	Xylene	×	△	×	◎
	Zinc acetate	◎	◎	×	
Z	Zinc chloride	◎	◎		◎
	Zinc sulfide	◎	◎	◎	